

ADVAGUM S.B.S.



DATASHEET

DESCRIPTION

ADVAGUM S.B.S. is a one part Bitumen Coating made From S.B.S., Rubberized modified bitumen. Cold applied and dries to a black high flexible membrane.

USES

membrane coating for wide application such as under ground concrete, Foundation, Retaining walls, Swimming pools, sheds and steel structures. Wet area like kitchen, bath rooms etc.

ADVANTAGES

All surface should be free from dust, oil, grease and loose material. The surface should be primed by ADVAPRIM D41 - and allow to dry before over coating. Stir ADVAGUM S.B.S. Rubberized Bitumen Coating will before use and apply minimum of two coats by brush or spray at the rate of 1.5-1Kg./ M2/ coat, Allow 24 hours between coats and apply each coat at right angles to the previous coat. To maximize durability and flexibility, the coating can be reinforced with a fiberglass tissue. Protect from rain and frost during curing.

TECHNICAL DATA	
Polymer	S.B.S. Rubber
Color	Black
Specific Gravity	0.98 g/ml
Viscosity	35000 - 45000
Solid Content	60%
Softening Point	<110°C
Elongation	1000%
Cold flex	-20°C

APPLICATION

Ensure that the surface to be treated is free from any loose particles, dust, oil, dirt, extra cement blocks and especially sand. Clean a second time, using a soft broom or a vacuum cleaner, to make sure that the surfaces are absolutely dust free.

HYDROSTATIC RESISTANCE

Water tight after 36 hours under 6m of water.

CHEMICAL RESISTANCE :

Resistance to water, alcohol, most salt solutions, available on soil and ground water some dilute acids and Alkalis.

CLEANING

Clean equipment with solvent immediately after use. If during application ADVAGUM S.B.S. Rubberized Bitumen Coating becomes thick dilute with aromatic solvent to make it easy for application. Place tools in solvent when not in use.

STORAGE

Store under cover in dry condition, highly inflammable.

HOW TO SPECIFY

The surface to be treated must be properly cleaned, two coats of ADVAGUM S.B.S. Rubberized Bitumen Coating must be used in accordance with the instructions of the manufacturer.

ADVAGUM S.B.S	
Packing	200 /20 L
Application Method	Brush / Roller / Spray
Form / Color	liquid / Black

The information given in this data sheet is based on both current development work and many years of field experience. Whilst every effort is made to ensure that the information is reliable, we cannot accept responsibility for any work carried out with our materials as we have no control over methods of application, site, conditions etc.



Al Mutathawir Insulation Materials Industries L.L.C.

T: + 971 6 534 5585 | F: + 971 6 534 7717 | P.O. Box: 22704 , Sharjah, U.A.E
E: info@aim-insu.com | W: www.aim-insu.com